

www.aithon.co.uk

CE



# AITHON A90H

fire protection of concrete structures Assessed by B.R.E.



bre

BRE Global Assessment Report

BS EN 13381-3 BS EN 12501-2

R240 on concrete slabs and walls

R120 on concrete beams and columns

REI 120 on hollow potted slabs

A FIRE TEST ON A CONCRETE SLAB

- FOR CONCRETE AND PRE-STRESSED CONCRETE
- WATERBORNE, LOW VOC COATING
- CLASSIFIED IN Y CLASS: NO NEED OF TOP-COATING EVEN IN HIGH HUMIDITY AND LOW TEMPERATURE INTERIOR ENVIRONMENT

AFTER FOUR HOURS OF FIRE TEST THE CHAR CREATED BY AITHON A90H STILL SHOWS AN IMPRESSIVE ADHESION TO THE CONCRETE SURFACE

hard, thin film intumescent coating for durable fire protection and decoration

# Up to 240 minutes fire resistance according to BS EN 13381-3 and BS EN 13501-2

The BS EN 13381-3 regards the fire resistance of concrete structures and the performance of the intumescent coatings applied on concrete are expressed in terms of **equivalent concrete** *thickness*. The method defines the quantities (in gr/m<sup>2</sup>) of intumescent coating required to achieve the same insulation performance provided by different thicknesses of concrete.

The calculation of the equivalent concrete thickness required for slabs and walls exposed to fire on one side is based on fire test results achieved on loaded slabs having minimum (500 gr/m<sup>2</sup>) and maximum (2035 gr/m<sup>2</sup>) applied quantity of intumescent coating. Linear interpolation between minimum and maximum is allowed.

AITH	ON A90H	Fire resistance time (min.) ( <b>exposed to fire on one side</b> )						
		30	60	90	120	180	240	
require g/m²	ed quantity mm DFT		Equiva	lent concr	ete thickne	ess (mm)		
500	0.25	12.5	10.4	8.3	5.4			
1080	0.54	26.0	32.0	27.0	16.0	13.0		
1500	0.75	26.6	35.8	33.7	25.6	22.0		
2000	1.00	29.5	40.4	41.7	24.7	32.6		
2390	1.19.	31.0	44.0	48.0	46.0	41.0	33.0	

The calculation of the equivalent concrete thickness required for beams and columns exposed to fire on three of four sides is based on fire test results achieved on loaded beams having minimum (500 gr/m<sup>2</sup>) and maximum (2092 gr/m<sup>2</sup>) applied quantity of intumescent coating. Linear interpolation between minimum and maximum is allowed.

AITHON A90H		Fire resistance time (min.) ( <b>exposed to fire on three or four sides</b> )					
		30	60	90	120		
required quantity g/m <sup>2</sup> mm DFT		Equivalent concrete thickness (mm)					
500	0.25	16.1	14.2	12.8			
	0.50	21.5	20.7	19.1	10.6		
1000		26.8	27.1	25.3	21.0		
1000 1500	0.75	20.0	<i>L</i> /./				



#### 30 years guarantee

Defining the lifetime of a fire protection system is often a difficult problem to solve. The over 30 years of our experience in research and development of intumescent coatings, together with the high quality of the row materials that we use, allow us to offer a 30 years guarantee for all our intumescent coatings and varnishes. For further details about our guarantee program please contact our technical service.

Aithon Ricerche International srl Via Mazzini 68 21020 Ternate (VA) – Italy Tel. +39 0332 964550 Fax +39 0332 964529 info@aithon.co.uk www.aithon.co.uk


19

ETA 13 / 0926

EAD 350402-00-1106

Fire protective product See ETA for relevant characteristics





### ENVIRONMENTALLY FRIENDLY

Waterborne, <u>melamine-free</u>, halogen-free, low VOC content, AITHON A90H protects concrete as well as the environment.

Thank to its very low emission to the environment, AITHON A90H is approved for the fire protection in clean rooms (Outgassing tests at 40°C: 2,6  $\mu$ g/g). This is a guarantee for any sensitive buildings like schools and hospitals.

Air emissions measured after 28 days were so low to guarantee Class A+ (ISO 16000), and most important, **is totally free from the carcinogenic melamine**.

## AITHON RICERCHE INTERNATIONAL s.r.l.

via Mazzini 68, I 21020 Ternate (VA) - Italia

info@aithon.co.uk www.aithon.co.uk Technical service: tel. +39-348-900-1515